



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 949 307 A1

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
13.10.1999 Bulletin 1999/41

(51) Int. Cl.<sup>6</sup>: C09D 151/08, C08F 251/00

(21) Application number: 99106611.9

(22) Date of filing: 31.03.1999

(84) Designated Contracting States:  
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE  
Designated Extension States:  
AL LT LV MK RO SI

(30) Priority: 08.04.1998 GB 9807426

(71) Applicant:  
IMPERIAL CHEMICAL INDUSTRIES PLC  
London SP1 3JF (GB)

(72) Inventors:  
• Horley, Susan, Mary  
Penn, Buckinghamshire, HP10 8JG (GB)  
• Wheeler, Stephen, Arthur  
Slough, Berkshire, SL1 2HP (GB)

(74) Representative:  
Cooper, Alan Victor  
Patents and Trade Marks Section  
Legal Affairs Department  
ICI Paints  
Wexham Road  
Slough, Berkshire SL2 5DS (GB)

(54) **Environmentally friendly aqueous architectural coating compositions**

(57) An environmentally friendly stable aqueous optionally structured water-resistant architectural coating composition (especially a paint) containing a film-forming binder polymer composed of a starch modified by the presence of carboxylic acid or inorganic carboxylate groups and bonded (probably grafted) to chains of copolymerised mono-ethylenically unsaturated monomers (e.g. "acrylic", "vinyl" or "styrenic" copolymers) permitting a stable aqueous dispersion of the binder polymer to be made which retains good water-resistance in the dried paint. The modified starch allows paints to be made with less dependence on materials obtained from non-renewable resources whilst retaining a low water-sensitivity.

EP 0 949 307 A1

## Description

[0001] This invention relates to environmentally friendly (optionally structured) aqueous architectural coating compositions, for example water-resistant paints (or varnishes or woodstains) suitable for use at ambient temperatures (say up to 35°C and usually above 0 or 5°C) in decorating surfaces of architectural structures such as buildings or furniture or fittings found in buildings. The invention allows starch to be used commercially in making these aqueous compositions so reducing their dependency on materials obtained from non-renewable resources such as petrochemicals. It also permits the use of smaller amounts of certain expensive co-monomers.

[0002] All aqueous architectural paints contain film-forming binder polymer. As a coating of liquid paint dries on a surface, this film-forming binder polymer serves to form a film (i.e. a dried coat) of paint which bonds to the surface and also binds together all the non-volatile components of the paint including particularly any pigments, opacifiers and extenders present.

[0003] A wide variety of binder polymers are available, but those most commonly used in aqueous architectural paints are of three broad types obtained from monoethylenically unsaturated monomers and known colloquially as the "acrylics", the "vinyls" and the "styrenics". The "acrylics" are usually copolymers of at least two alkyl esters of one or more mono-ethylenically unsaturated carboxylic acids (e.g. methyl methacrylate/butyl acrylate copolymer) whilst the "vinyls" usually comprise copolymers of a mono-vinyl ester of a saturated carboxylic acid and at least one of either an acrylic monomer or a different mono-vinyl ester. The "styrenics" are copolymers containing styrene (or a similar mono-vinyl aromatic monomer) together with a copolymerisable monomer which is usually an acrylic. Such binder polymers require the use of monomers which are obtained from petrochemical feedstocks whereas nowadays it is environmentally desirable to use as much as possible of material obtainable from renewable resources. In addition, some of the monomers essential to the binder polymer contain sterically bulky groups and are therefore relatively expensive.

[0004] Starch is one of the most abundant renewable resources because it is commercially available from such crops as potato, wheat, maize (both waxy and non-waxy), rice, sago, sorghum and tapioca. Moreover, it has been known since the 1960's that starch-containing film-forming polymer binders could be made by polymerising mono-ethylenically unsaturated monomers at ambient pressure in the presence of aqueous dispersions of starch whereupon binder polymers were formed which consisted of chains of polymerised mono-ethylenically unsaturated monomers chemically associated with the starch and this reduced the amount of material in the binder which comes from non-renewable resources. The precise nature of the association between the chains of polymerised monomers and the starch has not yet been unequivocally determined, but it is widely believed that the chains graft onto the starch. Such starch-containing binders have been used successfully in adhesives, in coating paper and in sizing textiles but instability problems led to phase separation and unpredictable increases in viscosity which meant that the starch-containing binders were not commercially suitable for use in making aqueous water-resistant architectural paints.

[0005] In 1981, British Patent Specification GB 2 075 525A disclosed that long term stability of aqueous dispersions of graft copolymers of starch and "vinyl" monomers could be improved by using a starch which had been modified by

a) subjecting it to acid and/or enzymatic hydrolysis either before or after the hydrolysis and

b) reacting the starch with molecules which bring about the positive introduction into the starch of (preferably non-ionic or cationic) groups such as carbamylethyl, alkyl, benzyl, benzalkyl, hydroxyalkyl, cyanoalkyl, acyl or dialkylamino alkyl groups.

Very stable aqueous dispersions of starch-containing film-forming binders were then obtained which GB 2 075 525A suggested could be used in adhesives, paper coating, textile sizing and in the making of water-based (i.e. aqueous) paints, although it did not disclose water-resistant architectural paints.

[0006] Starch-containing film-forming binders substituted with such specified non-ionic or cationic groups appear to have been very successful in the fields of adhesives, paper coating and textile sizing but they are not well suited for use in making aqueous water-resistant architectural paints owing to a high water-sensitivity as is illustrated by the loss of abrasion resistance which occurs when dried coats of the paints are subjected to the British Standards wet scrub resistance test described later. Water-sensitivity is of course a significant problem when a dried coat of paint is to be exposed to rain or frequent water-condensation.

[0007] A secondary disadvantage is that the conventional substituted starch binders are not very effective in creating the structure which is sometimes wanted in aqueous architectural paints, especially thixotropic paints. Structure can be created in various ways including an interaction between a so-called "structuring agent" (which is typically a titanium or zirconium chelate or a structuring clay) and the binder polymer plus any cellulosic thickener which may be present in the paint. Structuring days are clays such as laponite or bentonite clays. These three types interact in some way which is not fully understood to create a gel. Gel structures reduce the tendency for a paint to drip or splash and so they make painting less messy and allow brushes and rollers to be loaded with greater volumes of paint. During application of the

point to a surface by brush or pad, the paint experiences high shear forces which temporarily destroy the gel structure and allow the paint to be spread easily over the surface. This is known as "thixotropy".

[0008] A binder polymer for a modern aqueous architectural paint should preferably be capable of manufacture in conventional plants, nearly all of which operate at ambient pressure and it should be able to form aqueous dispersions which are stable under high shear forces such as are encountered during application of a paint by brush or pad. The paints should be environmentally friendly and able to give dried coatings which are sufficiently water-resistant to permit use outdoors or in humid locations such as found in kitchens and bathrooms. Accordingly, it is an object of this invention to provide an environmentally friendly aqueous coating composition which contains starch which has been modified to permit the formation of stable dispersions of binder polymer but which retains good water-resistance in the dried paint.

An optional object is to provide a starch-containing binder polymer which can be used in a thixotropic paint.

[0009] Accordingly, this invention provides an environmentally friendly (optionally structured and possibly thixotropic) aqueous architectural coating composition which includes film-forming binder polymer composed of modified starch chemically associated with chains of copolymerised monomers at least 93 wt % (and preferably 95 to 100 wt) of which are selected from mono-ethylenically unsaturated monomers wherein

a) the starch has been modified by the introduction of carboxylic acid groups optionally converted to an inorganic salt,

b) up to 50wt% of the starch-containing binder polymer is provided by the modified starch and

c) not more than 7 mol % (preferably 0 to 3 mol %) of the copolymerised monomers are derived from carboxylic acid monomers.

Granular amylopectin is the predominant form of starch in most natural sources and for this reason the starch prior to modification generally has a weight average molecular weight of at least  $5 \times 10^5$  and usually over  $1 \times 10^6$ . The preferred starches are obtained from potatoes, maize (corn) or from waxy maize. Potato and maize starch is relatively cheap and contains over 70wt% amylopectin whereas waxy maize starch is more expensive but contains even more (often over 90wt%) of amylopectin starch. Waxy potato starch also contains such higher levels of amylopectin but being a genetically modified product, it is not yet authorised for sale to the public.

[0010] The native starch is modified by subjecting it to a light oxidation sufficient to convert hydroxyl groups present in the native starch to carboxylic acid groups. The carboxylic acid groups introduced into the starch and also any acid groups which may be present in the copolymer chains may optionally be converted to alkali metal or ammonium salts and in practice the use of ammonium persulphate as a polymerisation initiator will lead to the presence of ammonium salts. Alternatively the adjustment of the pH of the coating composition by means of caustic soda will lead to sodium salts. However, ammonium salts are preferred because they are less harmful to water-resistance.

[0011] Light oxidation of the starch also causes a degree of chain scission which likewise introduces carboxylic acid groups likewise optionally converted to their inorganic salts. Light oxidation is simply and cheaply performed using oxygen from for example sodium hypochlorite or hydrogen peroxide. Preferably from 1 to 10 (especially 3 to 7) carboxylic groups per 100 glucose moieties are introduced and it has been found that this confers a long term stability on both the aqueous dispersions of binder and on the liquid paint which stability persists for at least 5 months whilst retaining a good water-resistance in the dried paint.

[0012] Carboxylic (i.e. carboxylic acid or salt) modification of the starch has also been found to enable the starch-containing binder polymer to be used in making structured paints. It appears that the introduced carboxylic groups promote some sort of interaction involving chelate or clay structuring agents with the result that when the structuring agents are introduced to the starch-containing binder, a gel structure forms which can confer thixotropy if enough structuring agent is present.

[0013] Preferably the starch-containing binder contains less than 30wt% (most preferably less than 20wt%) of the modified starch and less than 12wt% if very low water-sensitivity is wanted.

[0014] The starch-containing film-forming binder is preferably made at ambient pressure by dispersing the modified starch in cold water, heating the dispersion to about 70 to 95°C and then adding conventional free radical initiator such as ammonium persulphate to the aqueous dispersion and feeding in mono-ethylenically unsaturated monomers of the type conventionally used to make film-forming binder polymers for aqueous architectural paints. If preferred, a small amount of monomer and initiator can be added first to produce a seed and then the main charge of monomers and initiator can be added subsequently.

[0015] As indicated earlier, examples of suitable mono-ethylenically unsaturated monomers include:

a) "acrylics" such as alkyl (especially methyl, ethyl, ethylhexyl and n-butyl) esters of unsaturated carboxylic acids such as acrylic or methacrylic or fumaric acids or maleic anhydride,

b) "vinyls" such as mono-vinyl esters (especially vinyl acetate or vinyl "Versatate"<sup>1</sup>) and

c) "styrenics" which are usually styrene but which can be other monovinylidene aromatics such as vinyl toluene or vinyl pyridine and which are usually copolymerised with comonomers such as the ethyl or ethylhexyl or butyl acrylics mentioned above.

[0016] Various mono-ethylenically unsaturated acid or acid anhydride monomers may be copolymerised with the binder monomers to increase the hydrophilic character of the binder polymer in alkaline solutions and so increase the stability of the dispersions. However the acid comonomers must not exceed 7 mol % of the total monomers for otherwise the binder polymer becomes too hydrophilic to retain acceptable water-resistance. Suitable acids include unsaturated carboxylic acids and in particular acrylic or methacrylic acids and unsaturated acid anhydrides include maleic anhydride. If copolymerisation at superatmospheric pressures is commercially tolerable, the hydrophilic nature of the binder polymer can be adjusted downwards by including some mono-olefin (usually some ethylene) in the binder monomers.

[0017] It is desirable to choose combinations of monomers which include a sterically bulky monomer so as to result in starch-containing binder polymers in which the chain moieties have a glass transition temperature or "T<sub>g</sub>" as calculated using the Fox equation of below 350K and preferably below 325K. A T<sub>g</sub> temperature of below 270K may be necessary if it is desired to avoid using organic coalescing solvents. Preferred "acrylic" binder copolymers include copolymers of methyl methacrylate with butyl or 2-ethylhexyl acrylate as sterically bulky monomers and optionally copolymerised with up to 7 mol % acrylic or methacrylic acid. Preferred "vinyl" binder copolymers include copolymers of vinyl acetate with a bulky monomer which is usually vinyl "Versatate" or bulky acrylic monomer as above plus the same optional acid comonomers. Preferred "styrenic" binder copolymers include copolymers of styrene with butyl or 2-ethylhexyl acrylate serving as the bulky monomers with optionally up to 7 mol % acid comonomers as above. T<sub>g</sub> will be increased unacceptably by excessive crosslinking and so it is essential not to incorporate more than 7 wt % of a conjugated diene into the binder polymer and it is very much preferred to avoid any such diene. The presence of the free radical initiator at 70 to 90°C causes polymerisation of the unsaturated monomers to produce chains which are in some way chemically associated with the modified starch. Such association has been found to permit the use of a lower proportion of the sterically bulky monomers (which are relatively expensive) without loss of the ability to apply the paint at ambient temperatures.

[0018] Surprisingly, it has been found that the water-resistance of the dried coat of paint can be further increased by adding anionic surfactant to the aqueous dispersion of the modified starch even though surfactants usually cause water-sensitivity.

[0019] An aqueous dispersion of the starch-containing film-forming binder is easily converted into a coating composition by stirring it together with all the other components of the composition except for any chelate structuring agent. If a structured composition structured by means of a chelate is wanted, the chelate should be stirred in just before the composition is filled into cans so that the gel structure develops in the can. The most significant of the other components are pigments and opacifiers (usually rutile titanium dioxide or voided organic polymer particles) and also extenders which are solid particles which serve to space apart the pigments and opacifiers. Typical extenders are chalk, limestone, kaolin and talc. Silica may also be present as a milling agent. Whilst this invention is of most importance in making paints, it is also possible to omit the opacifier to produce a varnish or woodstain. The coating compositions preferably have a "Rothinmer" (low shear) viscosity of from 0.15 to 2.0 pascal.sec and a cone and plate (high shear) viscosity of from 0.03 to 0.5 pascal.sec all measured at 25°C using techniques specified later in this specification. A thixotropic structured composition preferably has a gel strength at 1 week of at least 50g.cm.

[0020] This invention also provides a process for making an environmentally friendly (optionally structured and possibly thixotropic) aqueous paint as described above which includes film-forming binder polymer composed of modified starch chemically associated with chains of copolymerised monomers at least 93 wt % (and preferably 95 to 100 wt %) of which are selected from mono-ethylenically unsaturated monomers wherein the process includes the steps of

a) modifying a starch by lightly oxidising it to introduce carboxylic acid groups, optionally converted to an inorganic salt,

b) adding free radical initiator to an aqueous dispersion of the modified starch and feeding the unsaturated monomers into the dispersion preferably in the presence of anionic surfactant,

<sup>1</sup> Vinyl "Versatate" is the vinyl ester of so-called "Versatic" acid which is a mixture of aliphatic monocarboxylic acids each containing an average of 9, 10 or 11 carbon atoms and is commercially available from the Shell Chemical Company of Carrington, England.

c) subjecting the dispersion to a temperature which causes copolymerisation of the monomers to produce chains of copolymerised monomers chemically associated with the modified starch so in turn creating the starch-containing film-forming binder,

d) mixing the binder polymer so produced with other components of the composition,

e) choosing the ratio of modified starch to unsaturated monomers so as to ensure that the weight of modified starch in the starch-containing binder does not exceed 50wt% of the weight of the starch-containing binder and

f) choosing a ratio of monomers such that not more than 7 mol % (preferably 0 to 3 mol %) of the copolymerised monomers are derived from carboxylic acid monomers.

This process can be successfully performed at ambient pressure provided that the co-monomers do not include monomers such as ethylene or 1, 3-butadiene which are gaseous under ambient pressures at the conventional copolymerisation temperatures.

[0021] The invention is further illustrated by the following Examples of which Examples A to C are comparative. In the examples:

[0022] Water-resistance was assessed in terms of loss of wet scrub resistance measured as the loss of paint in grams as determined according to British Standard BS 7719 1994 but when performed on dried coats of paint which are only 1 week old.

[0023] "Rotothinner" (low shear) viscosity is measured using the Sheen "Rotothinner" which is described in the Sheen Data Sheet on "Rotothinners" available from the address given below. Again measurements are performed at 25°C. "Rotothinner" viscosity corresponds to the viscosity of the paint when being poured from a can or loaded onto a brush.

[0024] Cone and Plate (high shear) viscosity is measured according to ASTM Test D 4287-88 at 25°C. Cone and Plate high shear viscosity corresponds to the viscosity of the paint when being applied by brush.

[0025] Gel Strength is measured using Sheen Gel Strength Tester supplied by Sheen Instruments Limited of Kingston Surrey England and described in their Data sheet Ref. 414. The measurement is performed at 25°C using a 4 x 2cm paddle.

#### EXAMPLE 1

Preparation of a Binder and a Paint when the starch is a Modified Potato Starch:

##### [0026]

##### a) Preparation of the Binder:

64g of a commercial modified starch which was a proprietary lightly oxidised granular potato starch believed to contain from 1 to 10 carboxylic acid groups per 100 glucose moieties was added via a funnel into 440g cold (20°C) water in a reflux flask together with 1.2g of sodium acetate buffer. The funnel was washed with a further 44g water which was added to the flask. The flask was heated with stirring to 85°C for 30 minutes to solubilise the starch.

The contents of the flask were allowed to cool to 67°C and then 37g of vinyl acetate monomer mixed with 9g vinyl "Versatate" monomer were added as binder monomers and the contents were stirred for 10 minutes. Next, 1.2g of ammonium persulphate initiator dissolved in water were added to the contents which were then heated to 80°C with stirring over a period of 35 minutes to produce a seed polymer. Then the temperature was raised to 85°C and 334g of vinyl acetate, 83g vinyl "Versatate" and 1.3g ammonium persulphate in water were added gradually with stirring to the flask over a period of 3 hours. During this time, the major proportion of the vinyl acetate/vinyl "Versatate" film-forming binder copolymer formed and grafted onto the modified starch. The carboxylic acid groups on the starch had been converted to the ammonium salt owing to the presence of ammonium persulphate.

Finally a further 0.54g of ammonium persulphate in water were added to the flask over a period of 10 minutes with continuing stirring at 85°C, in order to complete the copolymerisation and grafting process. The contents of the flask were then allowed to cool to 70°C and 1g t-butyl hydroperoxide in water was added. Further cooling to 60°C was allowed and 1g sodium metabisulphite was added followed by cooling to ambient (18°C) temperature. It was found that a stable aqueous dispersion of oxidised potato starch-containing vinyl acetate/vinyl "Versatate" film-forming binder copolymer containing 10wt% of the oxidised starch had been produced. The "vinyl" component of the starch-containing binder polymer had a theoretical Glass Transition Temperature (T<sub>g</sub>) as determined by the Fox equation of 303°K and the whole process was performed at ambient pressure.

##### b) Preparation of a Structured Paint:

The binder was converted into a structured architectural paint as follows:

A millbase was made up by stirring 69.7g particulate rutile titanium dioxide, 1.6g bentonite structuring clay and 15.3g particulate calcium carbonate extender into 88g of water containing 1.1g of polycarboxylate dispersant and 5.3g benzyl alcohol. Stirring was performed using a high speed stirrer operating at 3 000 rpm for 20 minutes. Stirring was then slowed to 300 rpm. 52g water and 3.2g cellulosic thickener were added gradually during a period of five minutes followed by stirring at 3000 rpm for 10 minutes.

[0027] Ammonia was added to 230g of an aqueous dispersion of the binder so as to produce a pH of 8. The millbase was then added gradually to the dispersion of binder copolymer over a period of 30 minutes with stirring at 300 rpm. After addition of the millbase, 30g "Ropaque" white voided organic pigment were stirred into the mixture followed by 2.5g of zirconium chelate structuring agent. The mixture was allowed to stand for 15 minutes and then was poured into cans where it developed a gel structure and became an aqueous structured architectural paint. The gel strength of the paint after 1 week and its viscosities were measured and the results are shown in Table 1 together with an assessment of its water sensitivity measured using the scrubbing technique of British Standard 7719:1994.

#### EXAMPLE 2 AND COMPARATIVE EXAMPLES A TO C

The Use of other Starch Types:

[0028] The procedure of Example 1 was repeated except the oxidised potato starch was replaced in turn by the following alternative starch types:

Example 2: Oxidised waxy maize starch

Comparative Example A: Enzyme degraded native potato starch.

Comparative Example B: Starch which had been subjected to substitution by hydroxypropyl groups as suggested by GB 2 075 525A

TABLE I  
PROPERTIES OF PAINTS MADE USING DIFFERENT  
TYPES OF MODIFIED STARCHES

Example	Starch Type	Gel Strength Pa.sec	Rotometer Viscosity (Low Shear) Pa.sec	Cone & Plate Viscosity Pa.sec (High Shear)	BS Water Scrub Resistance mg/cm <sup>2</sup>	Stability after 5 Months
1	Oxidised Potato	90	0.6	0.1	3.3	Stable
2	Oxidised Waxy Maize	70	0.5	0.1	2.8	Stable
3	Oxidised Potato plus anionic surfactant	130	0.5	0.1	1.6	Stable
A	Enzyme degraded potato	75	0.5	0.1	3.0	Flocculated
B	Hydroxy propylated Potato	30	0.5	Unstable	7.5	Unstable under high shear
C	*Conventional	130	0.6	0.1	1.9	Stable

Gel Strengths and Viscosities measured after 1 week

\*The conventional binder was a Vinyl Acetate/20wt% Vinyl "Versatate" copolymer

From Table 1, it can be seen that the hydroxypropylated starch-containing binder polymer could produce a gel strength

of only 30g/cm, showed a high water sensitivity and became unstable under high shear such as is encountered when a paint is brushed onto a surface. The dispersions and paints containing enzyme degraded potato starch were unstable and flocculated after 5 months.

## COMPARATIVE EXAMPLE C

[0029] An aqueous thixotropic paint was made up according to Part b) of Example 1 except that the starch-containing binder polymer was replaced by a conventional vinyl acetate/vinyl "Versatate" copolymer containing 20wt% of vinyl "Versatate".

## EXAMPLE 3

### The Use of Anionic Surfactant:

#### Preparation of Binder Polymer:

[0030] 55g of the modified potato starch of Example 1 was added via a funnel to 398g cold (20°C) water in a reflux flask together with 1.2g of sodium acetate and 4.9g of a proprietary anionic surfactant. The contents of the flask were heated to 85°C with stirring and 3.1g of ammonium persulphate in water were added. The temperature was maintained with stirring at 85°C for 30 minutes during which time mild degradation occurred. Then the temperature was allowed to fall to 65°C.

[0031] 46g of the vinyl acetate/vinyl "Versatate" mixture of Example 1 were fed to the contents which were held at 65°C for 10 minutes. 0.8g of ammonium persulphate in water were added and the temperature raised to 80°C with stirring over 35 minutes to produce a seed copolymer similar to that of Example 1 and again the carboxylic acid groups on the starch were converted to the ammonium salt because of the use of ammonium persulphate.

[0032] Having produced the seed copolymer, the procedure of Example 1 was then resumed except that 328g of vinyl acetate, 82g of vinyl "Versatate" and 4.9g of the anionic surfactant were added to produce a main bulk of copolymer which was slightly (but not materially) different to that of Example 1. The main bulk of the copolymer comprised 80 wt % vinyl acetate and 20 wt % vinyl "Versatate". It has been found subsequently that the proportion of vinyl "Versatate" can be reduced to 15 wt % with a corresponding increase to 85 wt % vinyl acetate without sufficiently affecting the Tg of the binder polymer to hinder application at ambient temperatures.

[0033] The starch-containing binder polymer obtained was then used to make a structured paint as in Example 1.

[0034] A dried coat of the paint produced was found to be more opaque than that of Example 1 and its water-sensitivity was found to have fallen substantially to give a British Scrub reading of only 1.6mg/cm<sup>2</sup> after 1 week.

## Claims

1. An environmentally friendly aqueous architectural coating composition which includes film-forming binder polymer composed of modified starch chemically associated with chains of copolymerised monomers at least 93 wt % of which are selected from mono-ethylenically unsaturated monomers wherein

a) the starch has been modified by the introduction of carboxylic acid or groups optionally converted to an inorganic salt,

b) up to 50wt% of the starch-containing binder polymer is provided by the modified starch and

c) not more than 7 mol % of the copolymerised mono-ethylenically unsaturated monomers are derived from carboxylic acid monomers.

2. A coating composition according to Claim 1 wherein the modified starch contains 1 to 10 carboxylic acid or salt groups per 100 glucose moieties.
3. A coating composition according to Claim 1 or Claim 2 wherein the modified starch is an oxidised potato or an oxidised maize starch.
4. A coating composition according to any one of the preceding Claims wherein the composition is structured.
5. A coating composition according to any one of Claims 1 to 5 wherein the composition is structured by means of a



titanium or zirconium chelate or a structuring clay.

6. A process for making a coating composition according to any one of the preceding Claims wherein the process includes the steps of

a) modifying a starch by lightly oxidising it to introduce carboxylic acid groups optionally converted to an inorganic salt,

b) adding free radical initiator to an aqueous dispersion of the modified starch and feeding the unsaturated monomers into the dispersion,

c) subjecting the dispersion to a temperature which causes polymerisation of the monomers to produce chains of copolymerised monomers chemically associated with the modified starch so in turn creating the starch-containing film-forming binder,

d) mixing the binder so produced with other components of the composition,

e) choosing the ratio of modified starch to unsaturated monomers so as to ensure that the weight of starch in the starch-containing binder does not exceed 50wt% of the weight of the starch-containing binder and

f) choosing a ratio of monomers such that not more than 7 mol% of the copolymerised monomers are derived from carboxylic acid monomers.

7. A process according to Claim 6 wherein the oxidation is performed using either hydrogen peroxide or sodium hypochlorite.

8. A process according to Claim 6 or 7 wherein the starch is a potato starch or a maize starch.

9. A process according to any one of Claims 6 to 8 wherein a structuring agent is added to the composition.

10. A process according to any one of the preceding Claims wherein the aqueous dispersion of modified starch also contains anionic surfactant.

European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 99 10 6611

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	EP 0 509 202 A (RHEOX INT) 21 October 1992 * claims 1,14 *	1-10	C09D151/08 C08F251/00
A	US 5 677 374 A (HAMUNEN ANTTI ET AL) 14 October 1997 * column 3, line 5-22 * * column 1, line 9 - column 17 *	1-3	
A	WO 90 09406 A (PENFORD PRODUCTS CO) 23 August 1990 * page 11, line 30 - page 12, line 17 *	1	
A	WO 93 21244 A (RAISION TEHTAAT OY AB HAMUNEN ANTTI (FI); ANTTILA MIKA (FI); NURM) 28 October 1993 * page 5, line 1-20 * * page 7, line 11-32 *	1	
A	US 5 055 541 A (FLOYD WILLIAM C ET AL) 8 October 1991 * column 2, line 49 - column 3, line 6 *	1	
A	US 5 003 022 A (NGUYEN CHARLES C ET AL) 26 March 1991 * column 4, line 52-55 *	1	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C09D C08F
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 11 June 1999	Examiner Meulemans, R
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 (03/99) (PUB/ON)

ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.

EP 99 10 6611

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

11-06-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0509202 A	21-10-1992	US 5164433 A	17-11-1992
		CA 2065223 A	18-10-1992
		DE 69219196 O	28-05-1997
		OE 69219196 T	07-08-1997
US 5677374 A	14-10-1997	FI 921752 A	17-10-1993
		AT 169940 T	15-09-1998
		CA 2117750 A	28-10-1993
		DE 69320495 D	24-09-1998
		DE 69320495 T	29-04-1999
		EP 0705285 A	10-04-1996
		ES 2122000 T	16-12-1998
		WO 9321244 A	28-10-1993
WO 9009406 A	23-08-1990	US 5003022 A	26-03-1991
		AT 131844 T	15-01-1996
		AU 621206 B	05-03-1992
		CA 5159190 A	05-09-1990
		CA 2025671 A,C	11-08-1990
		DE 69024275 D	01-02-1996
		DE 69024275 T	13-06-1996
		DK 411100 T	29-01-1996
		EP 0411100 A	06-02-1991
		JP 2875018 B	24-03-1999
		JP 3503908 T	29-08-1991
		NO 176610 B	23-01-1995
		PT 93121 A,B	31-08-1990
		US 5527544 A	18-06-1996
		US 5565509 A	15-10-1991
		US 5667885 A	16-09-1997
WO 9321244 A	28-10-1993	US 5130395 A	14-07-1992
		US 5130394 A	14-07-1992
		US 5416181 A	16-05-1995
		FI 921752 A	17-10-1993
		AT 169940 T	15-09-1998
US 5055541 A	08-10-1991	CA 2117750 A	28-10-1993
		OE 69320495 D	24-09-1998
		OE 69320495 T	29-04-1999
		EP 0705285 A	10-04-1996
		ES 2122000 T	16-12-1998
		US 5677374 A	14-10-1997
		EP 0405917 A	02-01-1991
		US 5116927 A	26-05-1992

EPO Form 182a

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.

EP 99 10 6611

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

11-06-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5003022 A	26-03-1991	AT 131844 T	15-01-1996
		AU 621206 B	05-03-1992
		AU 5159190 A	05-09-1990
		CA 2025671 A, C	11-08-1990
		DE 69024275 D	01-02-1996
		DE 69024275 T	13-06-1996
		DK 411100 T	29-01-1996
		EP 0411100 A	06-02-1991
		JP 2875018 B	24-03-1999
		JP 3503908 T	29-08-1991
		NO 176610 B	23-01-1995
		PT 93121 A, B	31-08-1990
		WO 9009406 A	23-08-1990
		US 5527544 A	18-06-1996
		US 5565509 A	15-10-1996
		US 5667885 A	16-09-1997
		US 5130395 A	14-07-1992
		US 5130394 A	14-07-1992
		US 5416181 A	16-05-1995

EPO FORM 1/98

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82